



Cempolatex Fibreflex

HIGHLY FLEXIBLE SELF-LEVELLING COMPOUND

TECHNICAL SHEET NO: TDS02237 24/03/2023

SMART ADVANTAGES

- Fibre-reinforced and highly flexible
- Rapid setting
- Suitable for use with underfloor heating

DESCRIPTION

Bostik Cempolatex Fibreflex is a protein-free, flexible self-levelling compound, reinforced with fibres. It has excellent workability and flow characteristics and can be trowelled to depths between 3mm and 30mm in a single application.

For smoothing and levelling sound, strong substrates where minimal vibration or lateral movement occurs. It can be laid over most common substrates including: concrete subfloors, sand/cement screeds, stone, anhydrite screeds, rigid metal, terrazzo & quarry tiles, asphalt and other strong, rigid subfloors.

It may also be used over sound, firmly bonded timber flooring such as 12mm flooring grade SP101 plywood and P5 chipboard, provided the timber is mechanically fixed. Bostik Cempolatex Fibreflex must not be used over adhesive or water-soluble residues.

As Bostik Cempolatex Fibreflex is totally protein-free, it is suitable for use in biologically sensitive areas. The low-odour formulation makes Bostik Cempolatex Fibreflex ideal for use in occupied buildings.

It is suitable for use with warm water underfloor heating systems and for encapsulating electrical radiant heating mats, provided a surface temperature of +27°C is not exceeded. It is not to be used as a wearing surface and should always be covered with a floor covering. For interior use only.



TECHNICAL CHARACTERISTICS

Colour	Grey
Form	Dry, free flowing powder
Specific Gravity	1.4 approx.
Composition	Blend of cements and fibres
Application Temperature	+5°C to +25°C
Gauging Liquid	Water
Application Thickness	3mm to 30mm
Working Times	Up to 20 minutes after mixing (depending on ambient temperatures)
Drying Times	Foot traffic: approx. 4 hours Loose lay floor coverings: approx. 8 hours Bond floor coverings: approx. 12 hours On non-absorbent subfloors lay floor coverings: approx. 24 hours (<3mm depth at +20°C, depending on ambient conditions)

*Depending on temperature, humidity, coating weight and substrate.

COVERAGE

- Approx. 4m² per bag at 3mm depth

(Depending on the smoothness of the floor surface & application technique)

APPLICATION

IMPORTANT: Before using Bostik Cempolatex Fibreflex, refer to the relevant Health & Safety Data Sheet, available at www.bostik.com/uk.

All phases of installation should comply with the latest editions of:

- BS 8102 Code of Practice for protection of structures against water from the ground.
- BS 5325 Code of Practice for installation of textile floor coverings.
- BS 8203 Code of Practice for installation of resilient floor coverings.
- BS 8201 Code of Practice for installations of for flooring of timber, timber products and wood-based panel products.

PREPARATION

Subfloor:

- Ensure the subfloor is sound, clean, dry and of adequate tensile and compressive strength, free from loose material, laitance, cracks and structural defects. Ensure there is an effective damp-proof membrane, which conforms to BS 8203.
- The subfloor should be tested in accordance with British Standards, using a properly calibrated and insulated hygrometer. A reading of 75% RH or less confirms that the subfloor is satisfactorily dry.
- Any contaminants that may hinder adhesion, such as grease, oil, dirt, dust, plaster, some curing compounds, surface hardeners, additives and adhesive residues must be completely removed.
- Any cracks or holes in the floor must be cleaned out and filled with Bostik Rapid Repair Mortar. Allowed to dry before applying Bostik Cempolatex Fibreflex.
- For optimum performance, a room temperature of +13°C to +18°C should be maintained for at least 24 hours prior to application. The temperature of the subfloor must be at least +5°C throughout the application and drying of the self-levelling compound. Ensure that a maximum room temperature of +25°C is not exceeded during application.

Underfloor heating systems:

- Warm water underfloor heating systems must be switched off for 48 hours before installation. Wait 48 hours after installation before gradually turning up underfloor heating.
- Electrical underfloor heating mats: Bostik Cempolatex Fibreflex may also be used to encapsulate electrical radiant underfloor heating mats. There must be a minimum of 5mm to 6mm Bostik Cempolatex Fibreflex covering the mat before bonding tiling products, and 10mm before bonding resilient textile or timber flooring. Install cabling as per manufacturer's instructions. Ensure the electrical cables are not damaged when installing the compound. The substrate to which the underfloor heating matting is fixed must be sound and stable.
- Electrical underfloor heating systems must be switched off for 48 hours before installation. Wait 7 days after

installation before gradually turning up underfloor heating.

Wooden surfaces:

- The timber substrate should be solidly fixed and clean, with open joints over laid with flooring grade plywood. The plywood must be sealed to prevent moisture ingress on the underside and all edges. The plywood should be sealed with Bostik Cempolay Universal Primer to stop the ingress of moisture. The timber must be a minimum of 15mm thick and screwed down at 300mm centres.

PRIMING

- In all cases, the subfloor must be primed prior to the application of the self-levelling compound, as shown in the table below. Priming of absorbent surfaces is recommended to prevent rapid drying of the self-levelling compound and minimise the formation of pinholes. See separate technical data sheets for primer application and drying details.

Absorbent substrates:	Bostik Cempolay Universal Primer (diluted 1:2 with water)
Dense/non-absorbent substrates including epoxy membranes:	Bostik Cempolay Universal or Bostik Epoxy Primer (for applications above 10mm)
Calcium sulphate screeds:	Contact Technical Services
Wooden floors (must be mechanically fixed):	Bostik Cempolay Universal Primer (diluted 1:2 with water)
Flooring grade mastic asphalt screeds:	Bostik Cempolay Universal Primer neat (for applications up to 5mm max)
Metal decking:	Contact Technical Services
Radiant underfloor heating systems:	Contact Technical Services

MIX RATIOS

- 4 litres of water to 20kg Bostik Cempolatex Fibreflex.

MIXING & APPLICATION DEPTH

- According to the mix ratio above, pour clean, cold water into a clean mixing bucket. Gradually add Bostik Cempolatex Fibreflex powder to the water, whilst continually mixing with an electric drill and mixing paddle until a smooth, lump-free mixture is obtained. This will normally be achieved after 2 minutes. Do not under mix. After mixing, a maturing time of at least 2 minutes is recommended.
- Do not mix more compound than you can use in 20 minutes. The mixture will remain workable for approximately 20 minutes under normal conditions. If the mix begins to stiffen before it has been spread, it must be discarded. Do not re-temper or add further water.
- Note: the addition of too much water may result in separation of the compound.
- Bostik Cempolatex Fibreflex can be applied from a minimum depth of 3mm, up to 30mm in a single application (5mm maximum total depth on mastic asphalt screeds and 10mm maximum depth on anhydrite subfloors).
- Any subsequent layers (up to a maximum combined depth of 30mm) are best applied as soon as the first layer is set for walking, but still damp. If it is dry, an intermediate primer coat of Bostik Cempolay Universal Primer (diluted

1:2 with water) is required.

APPLICATION

- Pour the mixed material onto the prepared subfloor in a continuous operation and allow to flow.
- Using a steel screeding trowel, spread evenly to the required depth and smoothness. Once laid, a second trowelling can be carried out after 15 to 30 minutes depending on site conditions.
- Protect surface from foot traffic prior to laying a floor covering. Ensure the compound is fully dry before applying a floor covering.

DRYING TIMES

- Protect freshly applied product from strong sunlight and through draughts, as this can dehydrate the product, resulting in incorrect curing. Also, protect from rain and frost. Do not force dry the self-levelling compound, as this may affect the curing process.
- Application in high temperatures may result in rapid setting and poor flow. The rapid loss of water may increase the risk of cracking.
- The drying time depends on how absorbent the subfloor is, the air humidity and both the ambient & floor temperatures.
- Under good site conditions, Bostik Cempolatex Fibreflex will normally take foot traffic 4 hours after application and loose lay floor coverings after approx. 8 hours. Leave at least 12 hours before applying bonded floor coverings. The walk on time and setting time will be delayed if the powder has been stored in temperatures below +10°C, or has been applied in temperatures below +20°C.
- The working and drying times of the compound will be reduced in higher temperatures and increased in lower temperatures.

CLEANING

- Clean tools and equipment with warm, soapy water immediately after use. Remove surplus compound from surfaces whilst it is still wet. Cured material can only be removed mechanically.

STORAGE

- Store and transport securely. Store for up to 6 months from date of manufacture in original, unopened packaging, clear of the ground, in cool, dry conditions within the temperature range +5°C to +25°C and out of direct sunlight. Protect from excessive drafts, frost, damp, condensation and dew.

PRECAUTIONS IN USE

- Do not use as a substitute for a DPM. An effective membrane is required to prevent water entering the system.
- Do not use a spiked roller, as this will pull fibres to the surface.
- The mix ratios and temperatures need to be followed accurately. Changing the mix ratios will disrupt the system and risk product failure.

- For any application not covered, please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.com/uk for advice.
- Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.
- For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data sheet for Bostik Cempolatex Fibreflex, available at www.bostik.com/uk.

PACKAGING

Product codes	30622897	20kg bag
---------------	----------	----------

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company that may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability that cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use that is inappropriate or use that is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Sales	Tel: 0844 371 1192	customer.service@bostik.com
Technical Advice	Tel: 0844 371 1197	technical.service@bostik.com
Safety Data Sheets	Tel: 01785 272625	sds.box-eu@bostik.com

DISCLAIMER

Bostik offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations.

The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bostik's research only. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contain herein.

Bostik Ltd
Common Road,
Stafford, ST16 3EH, UK
Phone: +44 (0)1785 272625
www.bostik.com/uk

BOSTIK HOTLINE

Smart help +44 (0)1785 272625



All advice, recommendations, figures and safety regulations provided are based on careful investigations, as well as the current state of our experience and are without obligation. Although the documentation has been compiled with the greatest care, we do not accept any liability for inaccuracies, mistakes, typesetting or printing errors. We reserve the right to modify the respective product if we deem it necessary. Since the design, the quality of the substrate and the processing conditions are beyond our assessment, no liability can be accepted for work performed on the basis of this documentation. We therefore advise you to carry out practical tests on site yourself. Our general Terms and Conditions of Sale and Delivery apply to all our sales and deliveries.